



**SECTION 1006**

**AGGREGATE FOR SURFACING**

**1006.1 Scope.** This specification covers aggregate to be used for surfacing.

**1006.2** Aggregate for surfacing shall be composed durable particles of rock or reclaimed concrete. When tested in accordance with AASHTO T 96, the wear shall not exceed 60 percent. The deleterious substances shall not exceed the following values and the sum of percentages of all deleterious substances shall not exceed 12 percent.

<b>Deleterious Material</b>	<b>Percent by Weight</b>
Deleterious Rock and Shale	12.0
Mud Balls	5.0
Other Foreign Material	2.0

**1006.3** Aggregate shall be in accordance with the following for the grade specified in the contract:

<b>Grade</b>	<b>Type of Material</b>	<b>Percent Passing</b>					
		<b>Sieve Sizes</b>					
		<b>1 in.</b>	<b>3/4 in.</b>	<b>3/8 in.</b>	<b>No. 4</b>	<b>No. 10</b>	<b>No. 200</b>
A <sup>a</sup>	Gravel	100	80-100	....	60 <sup>b</sup>	10-35	0-10
B <sup>a</sup>	Crushed Stone or Reclaimed Concrete	100	....	65 <sup>b</sup>	....	5-25	....
C	Chat	100	....	....	80 <sup>b</sup>	45 <sup>b</sup>	....

<sup>a</sup>Type 1 Aggregate for Base may be used, except all material shall be in accordance with [Sec 1007](#).

<sup>b</sup>Indicates maximum permitted.

**1006.4** If the quantity is of a size that makes sampling not practical, this material may be accepted on certification or visual inspection as allowed in [Sec 106.1.4](#).

**1006.4.1** If the quantity is less than 500 tons, a commercially available grade of aggregate may be accepted on certification or visual inspection.